

# Plastiverd BRIGHT

## Tech Polymer

March 2022, Version 01

Bright is a highly modified copolymer of PET (Polyethylene-Terephthalate), delivered in resin pellets. This resin has a very slow crystallization speed and is suitable for a wide range of general applications the main requirement of which is the even balance of optical and mechanical properties, such as: coated cardboards, displays, CD cases. It has a neutral tone colour and high transparency in thick cross sections.

SPECIFICATIONS			
Property	Unit	Value	Test Method
Intrinsic Viscosity	dL/gr	0'62 ± 0'02	LQ-M-001
Colour L	-	≥ 84	ASTM 6290
Colour b*	-	≤ 0	ASTM 6290

TYPICAL PROPERTIES			
Property	Unit	Value	Test Method
Specific Density Crystalline	g·cm <sup>-3</sup>	> 1'37	-
Crystallinity	%	> 30	-
Moisture	%	≤ 0'20	-
Bulk Density	Kg·m <sup>-3</sup>	840	-
Weight of 20 chips	mg	320	-
Melting Point	°C	225-235	-
Typical Moulding Temperature	°C	270-270	-
Drying Conditions - Temperature	°C	150-160	-
Drying Conditions - Time	h	5-6	-

All proper are measured under laboratory conditions by the analytical method shown. Method LQ-M-001 is based on ISO 1628. Different methods or conditions of analysis may give different values. Purchased material will be accompanied by Certificate or Analysis, with representative average values of specified properties.

**Food Contact Statement:** BRIGHT complies with the composition of requirements of the Regulation (EC) No 10/2011 and the EU directive on Packaging Waste (94/62/EC) and its amendments. For more information, contact your local Plastiverd representative.

*For queries or further information relating to this statement summary document please contact with Costumer Service*

[sac@plastiverd.com](mailto:sac@plastiverd.com)